

The new crystal clear, very strong and uv-b open greenhouse film



Product description	uv stable, 60 months in central Europe climatic conditions, seasonal use even longer		
Colour	crystal clear		
Thickness	180μ (tolerance +/- 5%, spot +/- 20%)		
Tensile Strength	EN ISO 527-3	MD 26 N/mm ²	TD 28 N/mm ²
Elongation at break	EN ISO 527-3	MD 550%	TD 650%
Dart drop	ISO 7765-1 (A)	Fold: >1000	flat:>1000
Total transmission	EN 2155-5	>91% (400-700nm)	
UV B transmission	Internal Test	>60 % (300-390nm)	
Light Diffusion	EN 2155-9	app. 18% (400-700nm)	
S/CL resistance	700/100 ppm		

Postadress:

TRÄDGÅRDSTEKNIK AB
Helsingborgsvägen 578, Varalöv
262 96 ÄNGELHOLM

Telefon : 0431-222 90
Bg.nr : 5743-7980
Org.nr : 556409-6120

URL:

www.tradgardsteknik.se
E-postadress:
info@tradgardsteknik.se